

紡織實驗室

修正報告

**Test Report** 報告號碼: TX62181 /2024 /SP 日期: 2024 年 07 月 17 日頁數: 四 之 一 頁

精采開發有限公司

桃園市觀音區大湖路二段 596 號

我們依照客戶的要求, 根據申請者送交的樣品進行測試如下:

樣品敘述 : 一塊針織布將用於迷彩內衣

顏色 : 迷彩

成份 : 100% Polyester

原產國家 : 台灣

申請者 : 精采開發有限公司

收件日期 : 2024 年 06 月 24 日

測試週期 : 2024 年 06 月 24 日至 2024 年 07 月 08 日

測試項目&amp;測試方法 : 依申請者要求進行下列測試

測試結果 : 請參照下一頁結果

備註: 此份報告, 已取代先前之報告號碼 TX62181/2024/SP, 日期 2024 年 07 月 08 日  
原因: 修正“成份”

台灣檢驗科技股份有限公司

張家豪

張家豪  
技術經理

"Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, and such sample(s) are retained for 1 months only." This test report cannot be reproduced, except in full, without prior written permission of the Company.

"This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>.  
Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law."

**Test Report** 報告號碼: TX62181 /2024 /SP 日期: 2024 年 07 月 17 日頁數: 四 之 二 頁

測試結果:

## 1. 纖維成份分析 (依中華民國國家標準 CNS 2339-1 L3050-1)

聚酯纖維 100%

## 2. 單位面積之質量 (依中華民國國家標準 CNS 13752 - L3243 6.4)

克/平方公尺 145.2

## 3. 破裂強度 (依中華民國國家標準 CNS 13752 L3243 6.17.1 Mullen 法)

超過 9.9 kgf/cm<sup>2</sup>

## 4. 耐氙弧燈光染色堅牢度 (依中華民國國家標準 CNS 3846 - L3075:2008 B 法-氣冷式, 直射法)

標準藍色布標 L3

## 5. 耐洗染色堅牢度 (依中華民國國家標準 CNS 1494 - L3027 - A-1 法, 水洗溫度 40°C)

變褪色 4-5 級

染污

棉纖維 4-5 級

聚酯纖維 4-5 級

自身污染度 4-5 級

備註: 級數依據 5 階灰色標評定, 1 為最差, 5 為最好

"Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, and such sample(s) are retained for 1 months only." This test report cannot be reproduced, except in full, without prior written permission of the Company.

"This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law."

**Test Report** 報告號碼: TX62181 /2024 /SP 日期: 2024 年 07 月 17 日頁數: 四 之 三 頁

測試結果:

## 6. 耐摩擦染色堅牢度 (依中華民國國家標準 CNS 1499 - L3032 - I 型)

	經向	緯向
乾式	4-5 級	4-5 級
濕式	4-5 級	4-5 級

備註: 級數依據 5 階灰色標評定, 1 為最差, 5 為最好

## 7. 耐汗染色堅牢度 (依中華民國國家標準 CNS 1496 - L3029)

	鹼性	酸性
變褪色	4-5 級	4-5 級
染污		
棉纖維	4-5 級	4-5 級
聚酯纖維	4-5 級	4-5 級
自身污染度	4-5 級	4-5 級

備註: 級數依據 5 階灰色標評定, 1 為最差, 5 為最好

8. 織物收縮率檢驗 (依中華民國國家標準 CNS 13752-L3243 6.30 - A 法 - 常溫水浸泡法 - 水溫  $25\pm 2^{\circ}\text{C}$  - 30 分鐘- 篩網乾燥- 洗一次)

縱向	+0.2%
橫向	+0.2%

備註: (+)表示收縮 (-)表示伸長

## 9. 織物吸水速度 - 滴下法 (FTTS-FA-004- 3.0 版次- 4.3)

	正面	背面
未水洗	< 1 秒	< 1 秒

"Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, and such sample(s) are retained for 1 months only." This test report cannot be reproduced, except in full, without prior written permission of the Company.

"This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law."

紡織實驗室

修正報告

**Test Report** 報告號碼: TX62181 /2024 /SP 日期: 2024 年 07 月 17 日頁數: 四 之 四 頁

測試結果:

10. 酸鹼值 (依國際標準組織 ISO 3071:2020)

6.6

備註: 萃取液 pH 值: 5.0 - 7.5  
萃取液溫度: 22±2°C

\*\*\* 結 束 \*\*\*

"Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, and such sample(s) are retained for 1 months only." This test report cannot be reproduced, except in full, without prior written permission of the Company.

"This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>.

Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law."